

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 60131993
PUBLICATION DATE : 13-07-85

APPLICATION DATE : 21-12-83
APPLICATION NUMBER : 58241680

APPLICANT : TOYOTA MOTOR CORP;

INVENTOR : OZAWA HITOSHI;

INT.CL. : C25D 3/56

TITLE : IRON-PHOSPHORUS ELECTROPLATING BATH

ABSTRACT : PURPOSE: To obtain an Fe-P electroplating bath giving an Fe-P film which does not crack by using bivalent Fe ions, hypophosphorous acid and/or hypophosphite and Al ions as essential components.

CONSTITUTION: This Fe-P electroplating bath contains 20~80g/l bivalent Fe ions, 0,01~15g/l (expressed in terms of $\text{NaH}_2\text{PO}_2 \cdot \text{H}_2\text{O}$) hypophosphorous acid and/or hypophosphite and 0.05~5g/l Al ions. To the plating bath may be added $\leq 200\text{g/l}$ electrically conductive salt such as ammonium sulfate or ammonium chloride, $\leq 60\text{g/l}$ pH buffer such as boric acid and $\leq 20\text{g/l}$ complexing agent for bi- or tervalent Fe ions such as acidic ammonium fluoride. The plating bath is preferably adjusted to 0.5~3.5pH. When an article is plated, the temp. of the bath is kept at room temp. ~80°C, and the current density of the cathode at 0.5~30A/dm².

COPYRIGHT: (C)1985,JPO&Japio